

A Review of the Application of Carbon Fiber Composites in Aircraft Engine Fan Blades

Haotian Rao

*Chang'an Dublin International College of Transportation at Chang'an University, Chang'an University, Xi'an, China
r13339101771@163.com*

Abstract. Compared to traditional titanium alloy blades, CFRP blades offer higher specific strength and specific stiffness, fatigue performance, and greater design flexibility in terms of structural geometry. This paper employs a literature review approach to discuss the theoretical foundations, engineering examples, limiting factors, and potential future developments related to CFRP resin-matrix composites. The analytical method first examines the principles of material reinforcement, damage tolerance, and the relationship between manufacturing methods and performance. Subsequently, composite fan designs from the GE90, GENx, GE9X, and Rolls-Royce families are studied as typical examples to illustrate their progression from experimentation to practical engineering applications. Furthermore, the advantages and challenges of CFRP fan blades are comprehensively summarized from the perspectives of mechanics, manufacturing, and maintenance. Finally, future research directions are proposed regarding smart manufacturing, multistage damage models, interface optimization, and multifunctional composite systems. This review demonstrates that carbon fiber-reinforced polymer fan blades have become an integral part of the new generation of aero-engines; however, manufacturing consistency, impact resistance, and life prediction still require further improvement.

Keywords: carbon fiber-reinforced polymer, aircraft engine fan blades, resin-matrix composites, damage tolerance, lightweight structures

1. Introduction

With ever-increasing demands for aviation efficiency, modern aircraft engines are evolving toward higher thrust-to-weight ratios, lower fuel consumption, and reduced environmental impact. As one of the largest components in high-bypass turbofan engines, the fan system has a significant impact on engine efficiency. Traditional titanium alloy fan blades have achieved high reliability after decades of development; however, their potential for further weight reduction and performance enhancement is gradually reaching its limits. Consequently, advanced composite materials have become a key research direction for future aircraft engine structures [1].

Carbon fiber-reinforced polymer-matrix composites (CFRP), with their excellent specific mechanical properties and anisotropic design capabilities, offer new solutions for lightweight fan

blade design. In terms of the material itself, composite systems allow fibers to be optimally aligned according to the applied loads, thereby fully utilizing the structural load-bearing capacity. At the same time, these resin-matrix materials are resistant to vibration-induced failure and exhibit good fatigue resistance, making them ideally suited for the manufacture of large fan blades that must withstand complex aerodynamic and centrifugal conditions [2].

Some fan blade tests conducted using carbon fiber-reinforced polymer (CFRP) have been well validated in engineering practice, but challenges remain. Technical challenges persist regarding how the material fails under impact loads, how forming processes affect manufacturing quality, and whether long-term performance can be accurately predicted. Therefore, it is necessary to conduct a systematic correlation analysis between the material's intrinsic properties, processing methods, structural characteristics, and actual service conditions.

This review focuses on three key areas: First, the theoretical mechanisms underlying the performance of CFRP fan blades, including performance enhancement, damage tolerance, and manufacturing methods; second, representative application examples and the current state of the art; and third, limitations and future research directions. Through literature analysis and comparative evaluation, this paper aims to provide a comprehensive account of the historical development of CFRP fan blades, while also offering a prospective analysis or technical recommendations regarding composite materials for aircraft engines.

2. Basic mechanisms and theoretical foundations of CFRP fan blade applications

2.1. Reinforcement mechanism and mechanical advantages of CFRP materials

The superiority of CFRP fan blades stems from the synergistic relationship between carbon fibers and the resin matrix. Therefore, the mechanical properties of composite materials depend not only on the intrinsic characteristics of each component but also on fiber orientation, interfacial bond quality, and the laminate structure [3]. Compared to metallic materials, carbon fiber-reinforced composites (CFRP) clearly exhibit significantly higher specific strength and specific stiffness. Consequently, it is conceivable that fan blades can be designed to be much larger without a significant increase in rotating mass. Reducing the weight of fan blades also lowers the load requirements on the surrounding engine structures (including the rotor system and containment structures), thereby yielding additional weight-saving benefits [4]. Another advantage is the design flexibility of carbon fiber materials. Carbon fibers can be arranged according to different stress conditions, enabling composite blades to achieve optimal load balance. High-strength fibers are suitable for areas with concentrated centrifugal stresses, while laminate structures can be used to improve either bending resistance or vibration resistance. However, the anisotropic properties of carbon fiber-reinforced composites (CFRP) also introduce complexity. Unlike isotropic metallic materials, composites respond differently to forces applied in different directions. Therefore, accurately predicting stress distribution and failure behavior requires multiscale analysis methods that integrate microscopic fiber behavior with macroscopic structural response [5]. Figure 1 illustrates this multi-scale architecture, encompassing the microscopic components (carbon fibres, the epoxy matrix and the fibre-matrix interface), the mesoscale laminate structure with customised fibre orientation, the macroscopic composite structural design, and the engineering performance achieved in fan blade applications.




Figure 1. Multiscale structure and reinforcement mechanism of carbon fiber-reinforced polymer composite fan blades

2.2. Damage tolerance mechanisms and failure behavior

Aviation engine fan blades are subjected to numerous extreme conditions, including foreign object impact, cyclic loading, temperature fluctuations, and aerodynamic vibrations. Damage tolerance is one of the fundamental and critical factors determining whether carbon fiber-reinforced polymer (CFRP) fan blades can replace traditional metal blades. The failure behavior of carbon fiber-reinforced composites (CFRP) differs from that exhibited by metal fatigue. Composites generally lack a stage of plastic deformation; damage manifests as a series of progressive forms (matrix cracking, fiber breakage or delamination, interfacial separation, etc.). These types of damage are interrelated and gradually degrade the structure [6]. To improve impact resistance, researchers have proposed numerous approaches: toughening epoxy resins, mixed fiber reinforcement, three-dimensional weaving techniques, and interfacial modification strategies. These measures are all aimed at preventing rapid crack propagation and increasing interlaminar toughness. For fan blades, bird strike resistance is a critical certification requirement. In the early days, Rolls-Royce and General Electric encountered obstacles when using composite materials for fan blades, namely that the materials did not provide adequate impact resistance. However, thanks to advancements in

carbon fiber technology, tougher resins, and more rational designs, composite fan blades were eventually accepted for use in commercial engines [7]. Consequently, the damage tolerance theory for carbon fiber-reinforced plastics (CFRP) is now shifting from a focus on simply using strong materials to a strategy of controlling damage progression. Contemporary designs typically balance stiffness, toughness, energy absorption efficiency, and failure prediction.

2.3. Manufacturing theory and the relationship between process and performance

If blades were made of metal using traditional machining or forging methods, the manufacturing process would be much simpler; in contrast, composite blades require a series of steps, including fiber placement, preforming, resin impregnation, curing, and surface treatment. Currently, automated fiber placement (AFP), resin transfer molding (RTM), and the newer weaving method have all been extensively studied in the manufacture of composite fan blades. AFP is a highly efficient process that allows for precise control of fiber orientation, making it a promising approach for the mass production of composites [8]. However, manufacturing defects remain a challenge. Bubbles, irregular fiber orientation, excess resin, or incomplete interfaces can all significantly reduce mechanical properties. Therefore, process simulation and nondestructive testing are indispensable in the development of composite fan blades. Recent research emphasizes the integration of material design, manufacturing simulation, and structural evaluation, rather than treating them as separate stages. This integrated approach can improve manufacturing consistency and reduce development costs.

3. Current applications and engineering case studies of CFRP fan blades

3.1. Development history of commercial carbon fiber-reinforced plastic fan blades

Carbon fiber-reinforced plastic (CFRP) fan blades for aircraft engines have now evolved from the experimental stage to relatively mature engineering applications. The earliest relevant efforts were conducted by Rolls-Royce in the 1970s during research on the RB211 engine. Although carbon fiber composites were used to manufacture blades at that time, their impact resistance did not meet requirements, resulting in failure to pass bird strike tests; titanium alloys remained the primary choice [7]. This failure demonstrated that high mechanical strength alone was insufficient to meet the demands of aircraft engine applications; composite fan blades required comprehensive optimization of material toughness, structural design, and impact protection. Engine development, epitomized by General Electric's (GE) GE90, achieved a major breakthrough in this field. By 1995, GE had, for the first time, deployed carbon fiber-reinforced epoxy resin blades in actual commercial aviation systems. The fan blades used in the GE90 were made from IM7-class carbon fiber combined with toughened epoxy resin, offering suitable strength and service life while significantly reducing weight [8]. The success of the GE90 demonstrated that carbon fiber-reinforced plastics (CFRP) can be an ideal material for large commercial turbofan engines and highlighted the promising future of composite fan development. Starting with the GE90, composite fan blades have continued to advance in the GEnx and GE9X engines. The composite fan and casing used in the GEnx have expanded the scale of such structures, demonstrating the potential for the effective use of larger composite areas in commercial engines. The latest-generation GE9X represents General Electric's fourth-generation composite fan blade design. By increasing carbon fiber stiffness and resin toughness, optimizing aerodynamic design, and adopting impact-resistant structures, the GE9X engine has achieved a larger fan diameter and a reduced number of blades. Compared to the 22

blades of the GE90 and the 18 blades of the GENx, the GE9X requires only 16 composite blades, representing a genuine improvement in structural efficiency. In addition to General Electric (GE), Rolls-Royce has also continued its exploration of composite fan blades. Its "UltraFan" project focuses on new composite materials, weight-reduction strategies, and modern manufacturing processes. This demonstrates that carbon fiber-reinforced plastic (CFRP) fan blades are no longer merely experimental but represent a direction that deserves serious consideration in the design of high-efficiency aircraft engines. The technical evolution milestones of commercial CFRP fan blades from the RB211 program to the GE9X engine are summarized in Figure 2.




Figure 2. Evolution of commercial CFRP fan blade technology from the RB211 to the GE9X

3.2. Analysis of application advantages and existing issues

The engineering success of carbon fiber-reinforced plastic (CFRP) fan blades stems primarily from their ability to simultaneously meet requirements for lightweight design and structural reliability. Compared to traditional titanium alloy blades, CFRP blades offer higher specific strength and specific stiffness, enabling designers to increase fan diameter while controlling rotating mass. A larger fan diameter improves bypass ratio and propulsive efficiency, thereby directly contributing to reduced fuel consumption and lower emissions [9].

Another important performance advantage is improved vibration characteristics. The polymer matrix used in CFRP materials inherently possesses significant damping capabilities, which helps reduce the transmission of vibrations during engine operation. This characteristic is particularly beneficial for large fan blades subjected to aerodynamic excitation and rotational imbalance. At the same time, composite materials are well-suited for overall structural optimization. By utilizing fiber orientation and laminate configurations, localized design reinforcements can be applied to areas experiencing high centrifugal forces and severe impacts. Traditional isotropic metals cannot achieve this with the same degree of flexibility. However, several limitations currently hinder their widespread adoption. The first challenge is resistance to impact damage. Although CFRP blades now handle bird strikes quite well, impact damage remains difficult to detect because delamination may occur internally without visible surface damage. Such defects are hard to identify and even harder to repair. The second challenge is manufacturing consistency. Composite structures are highly sensitive to parameters such as fiber placement, curing, resin condition, and even residual stress. Even minor manufacturing deviations can affect actual strength. Recent research on automated fiber

placement indicates that improving process stability and integrating simulation with manufacturing data are crucial for producing high-quality CFRP fan blades [10]. The third challenge concerns service life assessment. While there are well-established methods for damage analysis in metal blades, CFRP structures require more detailed monitoring. Existing nondestructive testing techniques—ultrasonics, acoustic emission, infrared, and digital imaging—have their uses but cannot guarantee accurate predictions of remaining service life [11].

4. Future development trends in CFRP fan blade technology

To address the three major challenges identified in Section 3.2—namely, manufacturing inconsistencies, impact-induced internal delamination damage, and the lack of reliable methods for predicting service life—future research should proceed simultaneously in three areas: intelligent manufacturing for process control, interface modification for damage tolerance, and multifunctional systems for real-time structural health monitoring.

4.1. Smart manufacturing and digital process optimization

In the future, the manufacturing of CFRP fan blades will gradually shift from experience-based production to smart manufacturing. Traditional composite manufacturing processes rely heavily on the technical skills of operators, particularly when handling fibers and addressing defects. However, as blade structures become larger or more complex, it becomes difficult to achieve consistent quality through manual labor alone. Even so, currently used automated layup methods still suffer from issues such as fiber waviness, layup defects, or process mismatches. Future research should integrate digital twins, artificial intelligence, and multiscale simulation methods to establish a closed-loop manufacturing system. By monitoring manufacturing parameters in real time and predicting mechanical properties, production processes can be optimized before defects occur. The resulting solutions should significantly reduce development costs for the next generation of composite fan blades while improving their performance.

4.2. Advanced materials and interface modification

For future carbon fiber-reinforced plastic (CFRP) fan blades, improvements should not only focus on making the carbon fibers more resilient but also analyze the interrelationships among the fibers, resin, and the fiber-matrix interface. The fiber-matrix interface determines stress transfer efficiency and damage propagation behavior. If the interface is too weak, premature delamination is likely to occur; if it is too strong, energy absorption capacity will be reduced. Therefore, interface modification methods involving nanomaterials, surface treatments, or multifunctional resins are expected to become important areas of research. At the same time, hybrid composites may offer additional advantages. Such designs can achieve a better balance between stiffness, toughness, and damage tolerance.

4.3. From lightweight structures to multifunctional composite systems

If they can simultaneously achieve functions such as sensing, structural monitoring, electrical conductivity, and thermal control, composite materials represent a very promising direction. Combined with smart maintenance methods, such designs hold promise for reducing repair costs and improving operational safety. However, there are currently no fully resolved solutions regarding the reliability of multifunctional composites, as well as their manufacturing and certification.

Therefore, future development should not only focus on material innovation but also be dedicated to establishing a comprehensive engineering evaluation system.



Figure 3. Proposal for the future development of CFRP fan blade technology

5. Conclusion

Carbon fiber-reinforced resin-based composites have become one of the most important materials in the development of modern aircraft engine fan blades. In terms of specific strength, specific stiffness, fatigue resistance, and structural adjustability, CFRP fan blades have proven to be excellent replacements for older metal structures and have successfully replaced traditional designs in various commercial aircraft engines.

From a theoretical perspective, the performance of such structures is determined by the combined effects of various factors, including the carbon fibers, resin, interfaces, and manufacturing processes. The reinforcement mechanism itself facilitates lightweight design, while damage tolerance theory provides guidance on achieving impact resistance and making accurate failure predictions. In terms of engineering practice, successful applications have been demonstrated in the GE90, GENx, and GE9X engines, and CFRP fan blades have proven to be reliable in commercial aviation. However, challenges remain to be addressed. Inadequate material manufacturing, internal damage, and limitations in life prediction and inspection methods continue to hinder the widespread adoption of these blades. Future development should focus on smart manufacturing, advanced interface engineering, multiscale simulation, and multifunctional composite material systems.

Current research limited by a heavy emphasis on theoretical discussions of materials and structures, while long-term operational data and comprehensive life-cycle assessments remain relatively scarce. Future research should leverage test results, numerical methods, and operational records to collectively support performance predictions—that is, to establish more accurate models. With continuous improvements in materials and manufacturing technologies, carbon fiber-reinforced plastic (CFRP) fan blades are expected to play an increasingly important role in sustainable and efficient aviation systems.

References

- [1] Soutis, C. (2005). Fiber-reinforced composites in aircraft manufacturing. *Advances in Aerospace Science*, 41(2), 143–151.
- [2] Baker, A. A., Dutton, S., & Kelly, D. (2004). *Composites for aircraft structures*. American Institute of Aeronautics and Astronautics.
- [3] Mallick, P. K. (2007). *Fiber-reinforced composites: Materials, manufacturing, and design*. CRC Press.
- [4] Campbell, F. C. (2010). *Structural composites*. ASM International.
- [5] González, C., Villatera, J. J., Molina-Aldaregia, J. M., López, C. S., & Lorca, J. (2017). Structural composites for multifunctional applications: Current challenges and future trends. *Advances in Materials Science*, 89, 194–251.
- [6] Wang, B., Zhong, S., Li, T. L., Fanxi, K. S., & Mi, J. (2020). Non-destructive testing and evaluation of composite materials and structures: A review of recent advances. *Advanced Manufacturing Technology*, 110, 1–29.
- [7] Marsh, G. (2012). Composites help reduce weight in aircraft engines. *Reinforced Plastics*, 56(6), 32–35.
- [8] GE Aviation. (2004). The new GENx engine takes the use of composites in jet engines to new heights. *GE Report*.
- [9] Soutis, C. (2020). Carbon fiber-reinforced plastics in aerospace engineering. *Composites B: Engineering*, 200, 108256.
- [10] Zhang, Y., et al. (2025). A review of automated fiber placement processes for composite fan blades in aircraft engines and a unit-scale feasibility study. *Composites Part B: Engineering*, 190, 108875.
- [11] Wang, B., Zhong, S., & Mi, J. (2020). Non-destructive testing techniques for aerospace composite structures: Challenges and future prospects. *Materials Today Communications*, 24, 101122.